



CL-CRETE® 150

*Polyurethane Alloy
Concrete Repair*

DESCRIPTION

CL-Crete® 150 is a two component, liquid applied, aromatic, polyurethane-alloy specifically designed to repair concrete and masonry substrates. The new surface will protect concrete from weather, corrosion, erosion, freeze/thaw spalling and chemical attack.

FEATURES

- ◆ Waterproof
- ◆ Excellent Abrasion Resistance
- ◆ Repairs Can Be Made in Hot or Cold Weather
- ◆ Rapid Cure Allows Traffic to Resume in 30 Minutes
- ◆ Remains Flexible in a Wide Range of Temperatures

TYPICAL USES

- ◆ Hairline Cracks
- ◆ Thin, Wide or Deep Cracks

COLORS

Part-A: Yellow, Part-B: Blue

PACKAGING

2 gallon kit: One 1 gallon can Part-A, one 1 gallon can Part-B

10 gallon kit: One 5 gallon pail Part-A and one 5 gallon pail Part-B

Contact Custom Linings for availability.

SURFACE PREPARATION

Hairline Crack Repair: Blow out the cracks with dry compressed air to remove loose and unsound material.

Large Crack Repair: Remove loose and unsound material in the crack by blowing the cracks with dry compressed air. Fill the cracks with sand that is at least twelve (12) mesh or larger.

APPLICATION

The volume mix ratio is 1 part Part-A to 1 part Part-B.

CL-Crete® 150 should be applied using a proportioning dispensing system. This type of system transfers, meters, and mixes the co-reactive Part-A and Part-B components at a very high rate and at the required proportions. It transfers from five or fifty-five gallon containers through proportioning pumps at the specified ratio of 1:1. Both components are pumped through a disposable static mixing tube with restrictor plugs. The combined mixture can then be dispensed into the gravel or sand prepared crack.

Material left in the static mixing tube will thicken in approximately 1 minute and solidify in 3 minutes. Static mixing tube should then be discarded.

TECHNICAL DATA

Hardness, ASTM D-2240	70 ± 5 Shore D
Tensile Strength, ASTM D-412	4000 ± 400 psi
	27.59 ± 2.7 MPa
Ultimate Elongation, ASTM D-412	7 ± 0.5%
Compressive Strength**, ASTM C-42	4750 psi
	32.76 kNm
Specific Gravity,	
Part-A	1.106
Part-B	0.947
Mixing Ratio by Weight	117:100
Mixing Ratio by Volume	1:1
Viscosity at 75°F (24°C), Brookfield,	
Part-A	20 ± 5 cps
Part-B	20 ± 5 cps
Pot Life @ 75°F (24°C)	80 seconds
Flash Point	>150°F
	>65.6°C
Bond Strength to Concrete	Excellent
Thermal Compatibility to Concrete	Good
**Compressive strength was checked on composite of Silica sand (12 mesh, 6.5 Moh's minimum hardness) and 18 to 20% of PC-Crete® 150 in a 4" X 8" cylinder.	

CHEMICAL RESISTANCE (Based on ASTM D-814)

PC-Crete® 150 was unaffected by the following chemicals:

Acidic Chemicals

- Acetic Acid, 1%
- Acetic Acid, 10%
- Hydrochloric Acid, 1%
- Hydrochloric Acid, 10%
- Sulfuric Acid, 1%
- Sulfuric Acid, 10%

Basic Chemicals

- Ammonium Hydroxide, 1%
- Ammonium Hydroxide, 10%

Oils, Fuels and Other Chemicals

- Hydraulic Oil
- Motor Oil
- Unleaded Gas (Regular)
- Unleaded Gas (Premium)
- Hexane
- IPA
- MIBK
- Xylene

CURING

CL-Crete® 150 is a rapid cure material that will be completely cured in approximately 3 minutes.

CL-Crete® 150 is very sensitive to heat and moisture. Higher temperatures and/or high humidity may slightly accelerate the cure time.

Low temperature and/or low humidity may slightly extend the cure time.

EQUIPMENT CLEANUP

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

STORAGE

CL-Crete® 150 has a shelf life of six (6) months from date of manufacture in original, factory sealed containers.

LIMITATIONS

Surfaces must be dry, clean and free of foreign matter.

Should be used in well-ventilated areas due to its strong odor.

Containers that have been opened must be used as soon as possible.

Do not dilute under any circumstance.

CL-Crete® 150 is for concrete crack repairs only. Slippery when wet.

Refer to general guidelines for more information.

WARNING

This product contains Isocyanates and Solvent.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Custom Linings representative or visit our website for current technical data and instructions.

LIMITED WARRANTY

Custom Linings warrants its products to be free of manufacturing defects and that they will meet Custom Linings current published physical properties. Custom Linings warrants that its products, when properly installed by a licensed applicator according to Custom Linings guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of three (3) years. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Custom Linings of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Custom Linings shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Custom Linings shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Custom Linings reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Custom Linings makes no claim that these tests or any other tests, accurately represent all environments.