

CHEMICAL COMPATIBILITY GUIDE

The information in this chart is intended only as a guide. This information has been compiled from various sources believed to be reliable. To verify compatibility or suitability of Custom Linings polyol coating for a specific application, the product should be tested under the specific service conditions - as chemical resistance can vary with temperature.

LEGEND

E = Excellent G = Good F = Fair P = Poor

MATERIAL RESISTANCE

Acetic Acid (10%)	E
Acetic Acid (concentrate)	P
Acetone	P
Alcohol	E
Ammonium Hydroxide	P
Automotive Gasoline	G
Automotive Oil	E
Aviation J.P. Fuels	E
Benzene	G
Boric Acid	E
Brine Solutions	E
Citric Acid (10%)	E
Diesel Fuel	G
Formic Acid (5%)	E
Formic Acid (10%)	P
Hydrochloric Acid (5%)	E
Hydrochloric Acid (45%)	F
Hydrogen Peroxide (10%)	E
Kerosene	E
Lactic Acid (45%)	F
Linseed Fatty Acid	E
Nitric Acid (10%)	E
Phosphoric Acid (50%)	E
Potash Lye (20%)	E
Saline Solution (30%)	E
Soda Solution (30%)	F
Sodium Hydroxide (10%)	P
Sugar Solution (30%)	E
Sulfuric Acid (25%)	E
Sulfuric Acid (50%)	F
Tannic Acid	E
Water	E